

Items		Unit	Inspection Method	Average Value
No.	Thickness	um	GBT6672-1986	175±5
1	Transmittance	%	ASTM D1003	≥76
2	Haze	%	ASTM D1003	2.5±1
3	Sheet Resistance	Ohm/sq	ASTM D991	15±2
4	Adhesive Property	B	ASTM D3359	5B
5	Pencil Hardness	H	GB/T6739-2006	/
6	Thermal Shrinkage	MD	ASTM D1204 (140°C 30min)	≤0.8
		TD		≤0.3
7	Warp	mm		